

## MATERIALSPEZIFIKATION

Producer: HOFFMANN MINERAL GmbH & Co. KG.  
 P.O. Box 14 60, D-86619 Neuburg (Donau),  
 Phone (+49-8431)53-0, Fax (+49-8431)53-3 30  
 Email: info@hoffmann-mineral.com

Commercial product name: **AKTISIL Q**

Chemical analysis: SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture  
 silica kaolinite  
 SILLITIN Z 86 coated with amino functional silane

Delivery form: Powder

Storage stability: minimum 2 years

Characteristics	Test method	Based on	Spezifikation
Brightness Y	UGR-PV/PT/69	DIN 53 163	82,0 – 87,0
Residue > 40 µm > 200 µm	UGR-PV/PT 43	DIN ISO 787 part 18	≤ 100 [mg/kg] ≤ 20 [mg/kg]
Volatile matter at 105°C RT 20°C / RH 50%	UGR-PV/PT 41	DIN ISO 787 part 2	≤ 0,4 [%]
Water content (Karl Fischer)	UGR-PV/PT 48	DIN 51 777	≤ 0,4 [%]
Concentration of additive	Mass balance		2,0 [%]
Water absorption (Baumann)	UGR-PV/PT 42		≤ 1,5 [%]
Air-jet screening method	UGR-PV/PT 84	DIN EN ISO 4610	≤ 0,3 [%]

Issued by	Approved by:
QA / Dirk Schröder	Head of R&D, QM / Dr. Christian Seeger

(automatically generated document – valid without signature)