

## MATERIAL SPECIFICATION

Producer: HOFFMANN MINERAL GmbH & Co. KG  
 P.O. Box 14 60 • D-86619 Neuburg (Donau)  
 Phone (+49-84 31) 53-0 • Fax (+49-84 31) 53-3 30  
 Internet: www.hoffmann-mineral.com  
 Email: info@hoffmann-mineral.com

Commercial product name: **AKTISIL VM 56 / 89**

Chemical analysis: SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture  
 silica kaolinite  
 SILLITIN Z 89 coated with 3-Vinylthriethoxy silane

Delivery form: Powder

Storage stability: Minimum 2 years

Characteristics	Test method	Based on	Specification
Brightness Y	UGR-PV/PT 69	DIN 53 163	82.0 – 87.0
Residue > 40 µm	UGR-PV/PT 43	DIN ISO 787 part 18	≤ 100 [mg/kg]
> 200 µm			≤ 20 [mg/kg]
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT 41	DIN ISO 787 part 2	≤ 1.4 [%]
Water content (Karl Fischer)	UGR-PV/PT 48	DIN 51 777	≤ 0.8 [%]
Concentration of additive	Mass balance		0.8 [%]
Air-jet screening method	UGR-PV/PT 84	DIN EN ISO 4610	≤ 0.3 [%]

Issued by:

QA / Dirk Schröder

Approved by:

Head of R&D, QM / Dr. Christian Seeger