

PRODUCT INFORMATION

TRACEL[®] IM 7200

PROD. NO. 185761



Chemical blowing agent

Appearance: white granules

Description: endothermic compound, polymer bound

Technical data:

decomposition temperature	135 - 220 °C
gas yield at 220°C related to blowing agent	abt. 120 ml/g
blowing agent content	70 %
bulk density	abt. 600 g/l

Dosage: extrusion and injection moulding of
PE, TPE, PP, PS, ABS and PPO 0,5 – 1,0 %

Properties: endothermic decomposition
the effective gas is CO₂

Storage: cool and dry

Packing: PE bags of 20 kg net, on one-way pallets of 800 kg net