

**PRODUCT INFORMATION**  
**TRACEL INC 4207 PS**

**Product no. 102606**



	Chemical blowing agent / nucleating agent	
Appearance	white granules	
Description	endothermic compound, polymer bound	
Technical data	decomposition temperature	135 - 220°C
	gas yield at 220°C related to blowing agent	abt. 120 ml/g
	blowing agent content	40 %
	bulk density	ev. 600 g/l
Dosage	extrusion and injection moulding of PS, ABS and SEBS	1,25 - 2,0 %
	nucleation of directly gassed PS	0,2 - 0,5 %
Properties	endothermic decomposition effective gas is CO <sub>2</sub>	
Storage	cool and dry	
Packing	PE-bags of 25 kg net, on one-way pallets of 1000 kg net	

Date of issue 22.09.2006

TRACEL® is a registered trademark

Our product information bases on tests to be reliable, however the recommendations are presented without guarantee. The data mentioned above are approximate figures, a product specification is available on request.

TRAMACO GmbH Siemensstraße 1-5 25421 PINNEBERG / GERMANY

Telephone: +49 4101-706-02 Telefax: +49 4101-706-200 Internet: www.tramaco.de E-mail: info@tramaco.de

